

Damage Repair Guidelines

Thermo-Ply™ Green, Red, Blue & AMG



Damage to Panel Description	Repair Guideline
Facer delaminations	Small Areas: Sheathing Tape (3M 8087 or equal) Large Areas: Liquid House wrap (StoGuard or equal)
Tears or holes in Thermo-ply less than 1" in length or diameter (non-structural)	4" Self-Adhering Flashing Tape meeting AMAA 711-07 (FortiFlash Butyl or equal)
Tears or holes up to 3" in length or diameter	Back with 2x6 blocking (min), fasten to blocking, and apply Self-Adhering Flashing Tape meeting AMAA 711-07 (FortiFlash Butyl or equal)
Tears or holes greater than 3" in length or diameter	Replace Panel

- These Guidelines should be used with good judgment to ensure sheathing maintains intended structural, moisture, & air barrier requirements.